

Technical Data Sheet

Plistix SR-90

Product # 12020

Available Internationally As:

Plico Stix SR-90

Product Description:

A high alumina, based, phosphate bonded, plaster type refractory servicing mix. Non wetting to aluminum alloys.

Standard Packaging: 50 # / 23 kg Pail

Shelf Life: 12 months

Service Limit: $3300\,^{\circ}\text{F}$ $1820\,^{\circ}\text{C}$ Contact Limit: $N/A\,^{\circ}\text{F}$ $N/A\,^{\circ}\text{C}$

Bulk Density - In Service: 160 pcf 2563 kg/m³

Bulk Density - To Place: 175 pcf 2804 kg/m³

Minimum Time To Firing: 0 hr

Water Range Per Standard Package		%	Quarts	Liters	
Vib Casting	min				
	max				
Casting	min				
	max				
Pumping	min				
	max				

Abrasion Loss after 1500°F / 815°C

per ASTM C704

N/A cc

Chemistry (calcined) %						
Al ₂ O ₃	87.7	Alk	0.2	MgO	0.1	
SiO ₂	7.6	TiO ₂	0.6	ZrO ₂		
CaO	0.1	P ₂ O ₅	2.7	Other		
Fe ₂ O ₃	0.7	SiC				

Coefficient of Thermal Expansion (reversable):

4.9 x 10^{-6} in/in/°F / 8.8 x 10^{-6} mm/mm/°C

Thermal Conductivity	btu*in/hr*ft²*°F	W/m°C		
500°F / 260°C	17.1	2.46		
1000°F / <i>540</i> °C	15.4	2.22		
1500°F / <i>815</i> °C	14.4	2.07		
2000°F / 1090°C	14.5	2.09		

Temperature				CS FM C133	Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C	Change% per ASTM C113	psi	MPa	psi	MPa	psi	MPa
230	110		1250	9.0				

Other Data: PREVENT MATERIAL FROM FREEZING: During cold weather this material must be shipped and stored in a warm place to prevent freezing. In warm weather, store in a cool dry place to prevent drying out.

Release Date: 1 Aug 2019

Heat Up Guide:

ASTM Class: C 673 90% Alumina

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.